

View Online at <https://aerobasegroup.com/nsn/5510-00-274-5296>

Species-grade And Grading Association:

Cedar, northern white no. 1 northeastern lumber manufacturers association or cedar, western no. 1 west coast lumber inspection bureau or cedar, western no. 1 western wood products association or douglas fir no. 1 west coast lumber inspection bureau or douglas fir no. 1 western wood products association or fir, balsam no. 1 northeastern lumber manufacturers association or fir, balsam no. 1 northern hardwood and pine manufacturers association or fir, subalpine no. 1 western wood products association or hem-fir no. 1 west coast lumber inspection bureau or hem-fir no. 1 western wood products association or hemlock, eastern no. 1 northeastern lumber manufacturers association or hemlock, eastern no. 1 northern hardwood and pine manufacturers association or hemlock, mountain no. 1 west coast lumber inspection bureau or hemlock, mountain no. 1 western wood products association or pine, eastern white no. 1 northeastern lumber manufacturers association or pine, eastern white no. 1 northern hardwood and pine manufacturers association or pine, idaho white no. 1 western wood products association or pine, jack no. 1 northeastern lumber manufacturers association or pine, jack no. 1 northern hardwood and pine manufacturers association or pine, lodgepole no. 1 western wood products association or pine, norway no. 1 northeastern lumber manufacturers association or pine, norway no. 1 northern hardwood and pine manufacturers association or pine, southern no. 1 southern pine inspection bureau or pine, sugar no. 1 western wood products association or redwood no. 1 redwood inspection service or spruce, eastern no. 1 northeastern lumber manufacturers association or spruce, eastern no. 1 northern hardwood and pine manufacturers association or spruce, engelmann no. 1 western wood products association or spruce, sitka no. 1 west coast lumber inspection bureau or tamarack no. 1 northeastern lumber manufacturers association or tamarack no. 1 northern hardwood and pine manufacturers association

Width-location And Measuring Method:

14.000 inches specified

Measuring Method And Length:

16.000 feet specified

Surface Condition Degree:

Surfaced four sides

Thickness-location And Measuring Method:

3.000 inches specified

Typical Wood Products Use:

Wedges and general construction

Special Features:

Dressed, air dried or kiln dried

Supplementary Features:

Unit of issue--bf

Specification Data:

81348-mm-l-751 government specification

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A173a0