

View Online at <https://aerobasegroup.com/nsn/5510-00-274-5375>

Random Width:

4 in. And wider, requiring 40 pct 8 in. Or wider

Species-grade And Grading Association:

Hardwood no. 2 construction boards national hardwood lumber association

Moisture Content Retention Percentage:

20.0

Random Length:

6 feet and longer, permitting 10 pct 6-9 feet and requiring 40 pct 14 feet or longer

Width-location And Measuring Method:

4.000 inches random

Measuring Method And Length:

6.000 feet random

Surface Condition Degree:

Surfaced two sides

Thickness-location And Measuring Method:

1.250 inches specified

Typical Wood Products Use:

Pallets, blocking and bracing

Supplementary Features:

Unit of issue bf

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A173a0