

View Online at <https://aerobasegroup.com/nsn/5510-00-274-7444>

Wood Producers Moulding Number:

8119

Species-grade And Grading Association:

Redwood clear redwood inspection service or pine, southern b and better southern pine inspection bureau or cedar, western mouldings west coast lumber inspection bureau or douglas fir mouldings west coast lumber inspection bureau or douglas-fir, south, interior standard western wood products association or fir, subalpine standard western wood products association or hem-fir standard western wood products association or hemlock, mountain standard western wood products association or larch standard western wood products association or pine, idaho white standard western wood products association or pine, lodgepole standard western wood products association or pine, ponderosa standard western wood products association or pine, sugar standard western wood products association or spruce, engelmann standard western wood products association

Moisture Content Retention Percentage:

15.0

Random Length:

N4 feet and longer, permitting a maximum of 10 percent of the contract line item qty to be furnished in 4 through 7 ft lengths and requiring a min of 60 percent of the item qty to b furnished in lengths of 12 ft and longer

Measuring Method And Length:

4.000 feet random

Typical Wood Products Use:

Interior and exterior trim

Style Designator:

Window & door stop

Supplementary Features:

Typical use--for interior and exterior trim, unit of issue--feet

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A173a0