

View Online at <https://aerobasegroup.com/nsn/5510-00-550-6820>

Species-grade And Grading Association:

Any acceptable no. 1 northeastern lumber manufacturers association or any acceptable no. 1 northern hardwood and pine manufacturers association or any acceptable no. 1 structural west coast lumber inspection bureau or any acceptable no. 1 western wood products association or pine, southern no. 1 sr timbers southern pine inspection bureau or redwood no. 1 structural redwood inspection service

Random Length:

10 ft and longer with a maximum of 10 pct to be 10 ft long and a min of 50 pct to be 14 ft and longer

Width-location And Measuring Method:

16.000 inches specified

Measuring Method And Length:

10.000 feet random

Surface Condition Degree:

Rough-unsanded full length

Thickness-location And Measuring Method:

16.000 inches specified

Typical Wood Products Use:

Beams, stingers, posts, columns and struts

Supplementary Features:

Unit of issue bf

Specification Data:

81348-mm-l-751 government specification

Specification Or Standard:

3 table

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A173a0