

View Online at <https://aerobasegroup.com/nsn/5510-00-550-6848>

Treatment Type:

Preservative, tt-w-571

Preservative Solution Type:

Ammoniacal copper arsenite or chromated copper arsenate, type i, ii or iii or coal-tar creosote or creosote coal-tar solution or creosote petroleum solution or pentachlorophenol in heavy petroleum solvent

Species-grade And Grading Association:

Douglas-fir, coastal no. 1 structural west coast lumber inspection bureau or douglas-fir, coastal no. 1 western wood products association or hemlock, western no. 1 structural west coast lumber inspection bureau or hemlock, western no. 1 western wood products association or larch no. 1 western wood products association or pine, southern no. 1 sr timbers southern pine inspection bureau

Random Length:

10 ft and longer with a maximum of 10 pct to be 10 ft long and a min of 50 pct to be 14 ft and longer

Width-location And Measuring Method:

14.000 inches specified

Measuring Method And Length:

10.000 feet random

Surface Condition Degree:

Rough-unsanded full length

Thickness-location And Measuring Method:

6.000 inches specified

Typical Wood Products Use:

Preservative treated beams, stringers, posts, timbers, columns and struts where creosote or oil-borne preservatives are required for use in fresh water ground contact

Service Usage:

Timbers and important structural members in contact with ground or fresh water

Supplementary Features:

Tt-w-571, table 1; unit of issue-bf

Specification Data:

81348-mm-l-751 government specification

Specification Or Standard:

3 table

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A173a0