

View Online at <https://aerobasegroup.com/nsn/5510-00-551-8687>

**Species-grade And Grading Association:**

Any acceptable clear redwood inspection service or any acceptable d finish southern pine inspection bureau or any acceptable d finish west coast lumber inspection bureau or any acceptable d select northeastern lumber manufacturers association or any acceptable d select northern hardwood and pine manufacturers association or any acceptable d select western wood products association or any acceptable prime finish western wood products association or any acceptable quality western wood products association

**Moisture Content Retention Percentage:**

15.0

**Random Length:**

4 ft and lomger with a maximum of 5 pct to be 4-7 ft, and a min of 50 pct to be 12 ft and longer

**Width-location And Measuring Method:**

8.000 inches specified

**Measuring Method And Length:**

4.000 feet random

**Surface Condition Degree:**

Surfaced four sides

**Thickness-location And Measuring Method:**

1.000 inches specified

**Typical Wood Products Use:**

Good quality finish for cornice trim, door and window casing and cabinet work

**Supplementary Features:**

See rulebooks for actual thk of select grades; unit of issue-bf

**Specification Data:**

81348-mm-l-751 government specification

**Specification Or Standard:**

I table

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A173a0