

View Online at <https://aerobasegroup.com/nsn/5510-00-551-8696>

**Species-grade And Grading Association:**

Any acceptable d select northeastern lumber manufacturers association or any acceptable no. 1 northern hardwood and pine manufacturers association or any acceptable d finish west coast lumber inspection bureau or any acceptable d finish western wood products association or any acceptable prime finish western wood products association or cedar, western b finish west coast lumber inspection bureau or pine, idaho white quality western wood products association or pine, southern d finish southern pine inspection bureau or redwood clear redwood inspection service

**Moisture Content Retention Percentage:**

15.0

**Random Length:**

4 ft and longer, max of 5 pct 4-7 ft and min of 50 pct to be 12 ft and longer

**Width-location And Measuring Method:**

10.000 inches specified

**Measuring Method And Length:**

4.000 feet random

**Surface Condition Degree:**

Surfaced four sides

**Thickness-location And Measuring Method:**

2.000 inches specified

**Typical Wood Products Use:**

Good quality finish for cornice trim, door and window casing and cabinet work

**Supplementary Features:**

Unit of issue-bf

**Specification Data:**

81348-mm-l-751 government specification

**Specification Or Standard:**

1 table

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A173a0