

View Online at <https://aerobasegroup.com/nsn/5510-00-551-9666>

**Species-grade And Grading Association:**

Any acceptable select structural northeastern lumber manufacturers association or any acceptable select structural northern hardwood and pine manufacturers association or any acceptable select structural west coast lumber inspection bureau or any acceptable select structural western wood products association or pine, southern select structural southern pine inspection bureau or redwood select structural redwood inspection service

**Moisture Content Retention Percentage:**

19.0

**Random Length:**

6 ft and longer, with a maximum of 1 pct to be 6-9 ft and a min of 4 pct to be 14 ft and longer

**Width-location And Measuring Method:**

12.000 inches specified

**Measuring Method And Length:**

6.000 feet random

**Surface Condition Degree:**

Surfaced four sides

**Thickness-location And Measuring Method:**

2.000 inches specified

**Typical Wood Products Use:**

Structural light framing, joists and planks for highest quality construction

**Supplementary Features:**

Unit of issue

**Specification Data:**

81348-mm-l-751 government specification

**Specification Or Standard:**

lii table

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A173a0