

View Online at <https://aerobasegroup.com/nsn/5510-00-551-9667>

Species-grade And Grading Association:

Any acceptable select structural northeastern lumber manufacturers association or any acceptable select structural northern hardwood and pine manufacturers association or any acceptable select structural west coast lumber inspection bureau or any acceptable select structural western wood products association or pine, southern select structural southern pine inspection bureau or redwood select structural redwood inspection service

Moisture Content Retention Percentage:

19.0

Random Length:

6 ft and longer with a maximum of 10 pct to be 6-9 ft and a min of 40 pct to be 14 ft and longer

Width-location And Measuring Method:

8.000 inches specified

Measuring Method And Length:

6.000 feet random

Surface Condition Degree:

Surfaced four sides

Thickness-location And Measuring Method:

2.000 inches specified

Typical Wood Products Use:

Structural light framing, joists and planks for highest quality construction

Supplementary Features:

Unit of issue bf

Specification Data:

81348-mm-l-751 government specification

Specification Or Standard:

3 table

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A173a0