

View Online at <https://aerobasegroup.com/nsn/5510-00-551-9729>

Species-grade And Grading Association:

Any acceptable 1 and 2 clear western wood products association or any acceptable b and better industrial clears west coast lumber inspection bureau or any acceptable b and better western wood products association or pine, idaho white supreme western wood products association or pine, southern b and better finish southern pine inspection bureau or redwood clear all heart redwood inspection service

Moisture Content Retention Percentage:

15.0

Random Length:

4 ft and longer, with a maximum of 5 pct to be 4-7 ft and a min of 50 pct to be 12 ft and longer

Width-location And Measuring Method:

8.000 inches specified

Measuring Method And Length:

4.000 feet random

Surface Condition Degree:

Surfaced four sides

Thickness-location And Measuring Method:

2.000 inches specified

Typical Wood Products Use:

Expensive high quality finish lumber for interior trim, door and window trim and cabinets

Supplementary Features:

Unit of issue--bf

Specification Data:

81348-mm-l-751 government specification

Specification Or Standard:

1 table

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A173a0