

View Online at <https://aerobasegroup.com/nsn/5510-00-551-9756>

Species-grade And Grading Association:

Any acceptable no. 1 northeastern lumber manufacturers association or any acceptable no. 1 northern hardwood and pine manufacturers association or any acceptable no. 1 western wood products association or any acceptable no. 1 sr timbers southern pine inspection bureau or any acceptable no. 1 structural redwood inspection service or any acceptable no. 1 structural west coast lumber inspection bureau

Random Length:

10 feet and longer, permitting 10 pct in 10 feet lengths and requiring 50 pct 14 feet or longer

Width-location And Measuring Method:

8.000 inches specified

Measuring Method And Length:

10.000 feet random

Surface Condition Degree:

Surfaced four sides

Thickness-location And Measuring Method:

6.000 inches specified

Typical Wood Products Use:

Beams, stingers, posts, columns and struts

Supplementary Features:

Unit of issue-bf

Specification Data:

81348-mm-l-751 government specification

Specification Or Standard:

lii table

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A173a0