

View Online at <https://aerobasegroup.com/nsn/5510-00-555-9081>

Species-grade And Grading Association:

Any acceptable 3 common northeastern lumber manufacturers association or any acceptable 3 common northern hardwood and pine manufacturers association or any acceptable 3 common western wood products association or any acceptable standard west coast lumber inspection bureau or pine, southern no. 2 boards southern pine inspection bureau

Moisture Content Retention Percentage:

19.0

Random Length:

2 ft and longer with a maximum of 5 pct to be 2-4 ft and min of 70 pct 10 ft and longer

Width-location And Measuring Method:

2.000 inches specified

Measuring Method And Length:

2.000 feet random

Surface Condition Degree:

Surfaced four sides or surfaced two sides and one edge

Thickness-location And Measuring Method:

1.000 inches specified

Typical Wood Products Use:

Cleat stock for boxes, furring strips and subflooring

Supplementary Features:

May be ripped from wider pieces which have been gradestamped-unit of issue-board foot

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A173a0