

View Online at <https://aerobasegroup.com/nsn/5510-00-813-2941>

Species-grade And Grading Association:

Douglas fir ungraded unrecognized or pine, southern ungraded unrecognized

Moisture Content Retention Percentage:

22.0

Width-location And Measuring Method:

3.750 inches specified

Measuring Method And Length:

6.833 feet specified

Surface Condition Degree:

Surfaced four sides

Thickness-location And Measuring Method:

2.750 inches specified

Typical Wood Products Use:

Line construction poles

Supplementary Features:

Unit of issue--each, for pony telephone arms

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

A173a0