

View Online at <https://aerobasegroup.com/nsn/5510-00-950-5814>

**Species-grade And Grading Association:**

Maple firsts national hardwood lumber association and maple seconds national hardwood lumber association

**Moisture Content Retention Percentage:**

17.0

**Width-location And Measuring Method:**

8.000 inches specified

**Measuring Method And Length:**

16.000 feet specified

**Thickness-location And Measuring Method:**

1.000 inches specified

**Typical Wood Products Use:**

Wedges and general construction

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A173a0