

View Online at <https://aerobasegroup.com/nsn/5510-00-950-5816>

Species-grade And Grading Association:

Maple firsts national hardwood lumber association and maple seconds national hardwood lumber association

Moisture Content Retention Percentage:

17.0

Width-location And Measuring Method:

8.000 inches specified

Measuring Method And Length:

16.000 feet specified

Thickness-location And Measuring Method:

4.000 inches specified

Typical Wood Products Use:

Wedges and general construction

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A173a0