

View Online at <https://aerobasegroup.com/nsn/5610-00-530-3632>

Usage Design:

Roofing

Minimum Flash Point:

347.0 degrees fahrenheit

Content Within Each Unit Package:

150 lb

Basic Formulation Type:

Penetration

Penetration Range:

20 to 50 hundredths cm at 77 degrees f, 100 gm load and 5 sec duration

Penetration Softening Range:

+150.0 to 165.0 degrees fahrenheit

Mineral Filler:

Not included

Specification Or Standard:

2 type and 1 grade and a class

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fig:

T379-c