

View Online at <https://aerobasegroup.com/nsn/5610-00-530-3634>

Usage Design:

Primer for bonding and primer for roofing

Minimum Flash Point:

347.0 degrees fahrenheit

Content Within Each Unit Package:

55 gal

Basic Formulation Type:

Penetration

Penetration Range:

15 to 50 hundredths cm at 77 degrees f, 100 gm load and 5 sec duration

Penetration Softening Range:

+131.0 to 170.0 degrees fahrenheit

Mineral Filler:

Not included

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

T379-c