

View Online at <https://aerobasegroup.com/nsn/5821-01-065-1898>

End Application:

Afsatcom ii

Precious Material:

Silver

General Description:

Matl beryllium copper cond 1/2 hm alloy 0.0100 in. Thk; finish silver plate 0.0002 min. Thk grade a per qq-s-365; temp range m65 to p125c; knoop hardness number 240 min. Using knoop indenter with 500 gram load; has 20 cavities; dimensions 0.753 in. By 0.426 in. By 0.776 in.

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli