

View Online at <https://aerobasegroup.com/nsn/5950-01-047-1345>

Special Features:

Matl ferrite medium permeability, initial perm at 20deg c 250 uo, flux density at 20deg c 3300 gauss, saturation value 4200 at h=2000 oe and 20deg c, o/a diameter 0.220 in., 2 holes 0.035 diameter thru

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A515h0