Electromagnetic Component Core - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/5950-01-273-8064

Unpackaged Unit Weight:

0.300 ounces

Special Features:

Electrical characteristic, initial permeability, 5000 percent; effective permeability, 3800 percent; saturation flux density, 3600 gauss at 2

oersteds; coercive force, 0.08 oersted

Material:

Ferrite

Material:

Ferrite

Surface Treatment (non-core):

Phosphate coated

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

T143-c