Electrical Insulation Sleeving - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/5970-00-866-3034

| Reliability In | ndicator: |
|----------------|--|
| Not establish | |
| Overall Len | qth: |
| Any accepta | |
| Tempuratur | |
| | es celsius and 135.0 degrees celsius |
| - | ntal Protection: |
| Corrosion re | sistant and flame resistant and mildew resistant and water resistant |
| Expanded I | nside Diameter: |
| 0.093 inches | 3 |
| Recovered | Inside Diameter: |
| 0.046 inches | 3 |
| Recovered | Wall Thickness: |
| Between 0.0 | 117 inches and 0.023 inches |
| Heat Shrink | age Rating In Percent: |
| 50.0 | |
| Min. Tensile | e Strength (psi): |
| 1500 pounds | s per square inch |
| Flexibility: | |
| Flexible | |
| Color: | |
| Blue | |
| Material: | |
| Plastic, poly | volefin, mil-i-23053/5, class 1 |
| Material: | |
| Plastic cross | s-linked polyolefin |
| Style Desig | nator: |
| Shrinkable | |
| Dielectric M | laterial Voltage Rating Per Unit Thickness: |
| 500.0 volts p | per military /0.001 inch/ |
| Shelf Life: | |
| N/a | |
| Unit Of Mea | sure: |
| | |
| Demilitariza | ition: |
| No | |
| Fiig: | |
| A22500 | |