

View Online at <https://aerobasegroup.com/nsn/6520-01-087-8564>

Hardness Designation:

Hard

Chemical Composition Percentage:

47.0 gold, 6.5 palladium

Weight:

20.0 pennyweight per plate

Special Features:

Dtype iii; yellow color; micro-fine; melting range 1590 to 1675 degrees f.; casting temperature 1800 degrees f.; vickers hardness 138 quenched, 230 hardened; for crown and bridge work; 1 oz. Package

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

T243-d