

View Online at <https://aerobasegroup.com/nsn/6520-01-087-8566>

Hardness Designation:

Not rated

Chemical Composition Percentage:

52.0 gold, 38.0 palladium

Weight:

20.0 pennyweight per plate

Special Features:

Dwhite color; silver free; micro-fine; melting range 2250 to 2300 degrees f.; vickers hardness 225; casting temperature 2450 degrees f.; ceramic alloy for porcelain-to-gold technique; 1 oz. Package

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

T243-d