

View Online at <https://aerobasegroup.com/nsn/6520-01-371-9652>

Compression Strength:

15000.0 pounds per square inch

Usage Design:

Bridge restoration and crown restoration and denture relining

Setting Time:

Between 10 minutes and 13 minutes

Tint Color:

Blue

Product Name:

Stone artificial den bridge&crown blue 60g/packet 144s

Special Features:

Water powder ratio ml/g 21: 100; glazed surface; compatible w/all impression materials; unit pkg qty c/o: 144 pre-measured 60 g packets

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

T243-d