

View Online at <https://aerobasegroup.com/nsn/6520-01-481-4033>

Usage Design:

Any acceptable

Setting Time:

2 hours

Product Name:

Investment dental 2hrs setting time 60g packages 150s

Special Features:

5cera-fina carbon free fine grained investment for high fusing alloys; 8--10 minute working time; 0.25% setting expansion; 1.3% thermal expansion; compressive strength wet is 600psi (4mpa); 144 each 60 gram packages of powder and 2 liters of liquid

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

T243-d