

View Online at <https://aerobasegroup.com/nsn/6520-01-565-1813>

**Compression Strength:**

14000.0 pounds per square inch

**Usage Design:**

Bridge restoration and crown restoration

**Setting Time:**

Between 8 minutes and 9 minutes

**Special Features:**

Type iv vel-mix die stone; hi strength, lo expansion crown and bridge die stone which produces smooth, hard, accurate surfaces; pink sugg; 20 ml per 100 grams powder; calcium sulfate and gypsum; 0 to 0.1 pct setting expansion; avoid contact w/acids; odorless; noncombustible, slightly water soluble

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

T243-d