

View Online at <https://aerobasegroup.com/nsn/6520-01-565-1813>

Compression Strength:

14000.0 pounds per square inch

Usage Design:

Bridge restoration and crown restoration

Setting Time:

Between 8 minutes and 9 minutes

Special Features:

Type iv vel-mix die stone; hi strength, lo expansion crown and bridge die stone which produces smooth, hard, accurate surfaces; pink sugg; 20 ml per 100 grams powder; calcium sulfate and gypsum; 0 to 0.1 pct setting expansion; avoid contact w/acids; odorless; noncombustible, slightly water soluble

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

T243-d