

View Online at <https://aerobasegroup.com/nsn/6520-01-581-2120>

Compression Strength:

4000.0 pounds per square inch

Setting Time:

10 minutes

Weight:

25.0 pounds

Tint Color:

Buff

Product Name:

Stone artificial dental quickstone buff 25lb

Special Features:

Consistent handling properties; may be used for a variety of lab procedures; water/powder ratio: 28 ml/100 g; working time: 3-5 min; setting time: 10 min; setting expansion: 0.14 pct; compressive strength, wet (1 hr): 4000 psi; compressive strength, dry (48 hr): 8000 psi; buff; iso type 3; 25 lb (11 kg) package

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

T243-d