

View Online at <https://aerobasegroup.com/nsn/6520-01-581-2120>

**Compression Strength:**

4000.0 pounds per square inch

**Setting Time:**

10 minutes

**Weight:**

25.0 pounds

**Tint Color:**

Buff

**Product Name:**

Stone artificial dental quickstone buff 25lb

**Special Features:**

Consistent handling properties; may be used for a variety of lab procedures; water/powder ratio: 28 ml/100 g; working time: 3-5 min; setting time: 10 min; setting expansion: 0.14 pct; compressive strength, wet (1 hr): 4000 psi; compressive strength, dry (48 hr): 8000 psi; buff; iso type 3; 25 lb (11 kg) package

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

T243-d