NSN 6640-01-075-1736

Laboratory Specimen Preparation Press - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/6640-01-075-1736

General Description:

No Fiig: A23900

Press is designed to produce high quality metallographic mounts, using any of the following compression powers phenolic resin, diallyl phthalate, plastimet, transoptic; heat is provided by a thermostatically controller heater which may be removed for faster cooling of the mold; pressure is applied by turning the knob clockwise to its furthest travel and operating the pump handle up and down stroke; heater preset at 302 degrees f, 150 degrees c under actual molding condition, heater maybe readjusted, press works at 220 volts

302 degrees f, 150 degrees c under actual molding condition, heater maybe readjusted, press works at 220
Shelf Life:
N/a
Unit Of Measure:
Demilitarization: