

View Online at <https://aerobasegroup.com/nsn/6810-00-546-4853>

General Description:

Percent total tin min 28.0 pct, pct stannous tin min 27.0 pct, color gardner 5 , pounds/gallon 80 degrees f 10.40 to 10.65, specific gravi type 80 degrees f 1.250-1.280, viscosity 80 degrees f gardner p 4.00 poises, nuocure 28 is a stannous 2-ethylehexoate in a clear liquid form which is solvents, nuocure 28 is an excellent catalyst for one shot polyurethane foam process

Reference Number Differentiating Characteristics:

50 lb can

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No