

View Online at <https://aerobasegroup.com/nsn/6810-01-263-7487>

**General Description:**

Contains polytetrafluoroethylene tfe fibers; tensile strength (5.1 mm/min) at 23 degrees c: 52.4; modulus of elasticity (5.1 mm/min) at 23 degrees c: 2894; melting point: 175 degrees c; specific gravity: 1.54

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No