

View Online at <https://aerobasegroup.com/nsn/6810-01-587-3501>

Special Features:

2.3 g/cc apparent density; >3500 psi bond strength; 400-600 uin ra surface roughness; 730 rc hardness; 2000 degrees f operating temperature; 50 s/50g hall flow; -140 mesh + 15um size distribution; spray dired and sintered yttria stabilized zirconia for thermal barrier coatings

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No