

View Online at <https://aerobasegroup.com/nsn/7230-01-497-6896>

End Application:

C130j

General Description:

Sbase cloth weight 1.6 oz per sq yd; finished weight 4.5 oz per sq yd; breaking strength, grab method 5100 warp and fill 125 lbs min; tearing strength, tongue method 5132, warp 7 lbs min, fill 6 lbs min; flame resistance self extinguishing per method far 25853 par. B; abrasion resistance method 5306 taber, cs-17 wheels, 250 g load min, cyclesto produce 1/4 in tear 1250; moisture permeability grains per sq ft per hour per inches height maximum when tested in accordance to astm d783-44t 1.75

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No