NSN 8010-00-052-5112

Primer Coating - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/8010-00-052-5112

| View Online at https://aerobasegroup.com/nsn/8010-00-052-5112 |
|--|
| Application Method: |
| Brushing as packaged or roller or spraying as is |
| Content Within Each Unit Package: |
| Consists of 1.73 gallons of component a in 3 gallon container and 60 lbs of component b (zinc dust) |
| Pigment Material Type: |
| Zinc dust |
| Pigment Separate Package Type: |
| Container |
| Rated Drying Time: |
| 20.000 minutes |
| Volatile Organic Compound In Grams Per Liters: |
| 340.0 |
| Special Features: |
| Moisture curing; for low temperature application to blast cleaned or power tool cleaned steel surfaces |
| Color: |
| Gray |
| Shelf Life: |
| N/a |
| Unit Of Measure: |
| |
| Demilitarization: |
| No |
| Fiig: |
| A09700 |
| |