

View Online at <https://aerobasegroup.com/nsn/8010-00-138-8545>

Application Method:

Spraying as is

Quantity Within Each Unit Package:

1.000 gallons

Content Within Each Unit Package:

Consists of component a and component b to equal 1 gallon

Volatile Organic Compound In Grams Per Liter:

772.0

Special Features:

Fluorocarbon dry film lubricant; for metal and rubber substrates; for service temperatures up to 150 degrees c (continuous) and 160 degrees c (intermittent); cures in 60 minutes at 160 degrees c or 30 minutes at 180 degrees c or 10 minutes at 200 degrees c; color changes from blue to green when cured; resistant to oils, alcohols, ketones, chlorinated hydrocarbons, dilute acids, esters, aromatic hydrocarbons and gasohol

Color:

Green

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A09700