

View Online at <https://aerobasegroup.com/nsn/8010-00-138-8545>

**Application Method:**

Spraying as is

**Quantity Within Each Unit Package:**

1.000 gallons

**Content Within Each Unit Package:**

Consists of component a and component b to equal 1 gallon

**Volatile Organic Compound In Grams Per Liter:**

772.0

**Special Features:**

Fluorocarbon dry film lubricant; for metal and rubber substrates; for service temperatures up to 150 degrees c (continuous) and 160 degrees c (intermittent); cures in 60 minutes at 160 degrees c or 30 minutes at 180 degrees c or 10 minutes at 200 degrees c; color changes from blue to green when cured; resistant to oils, alcohols, ketones, chlorinated hydrocarbons, dilute acids, esters, aromatic hydrocarbons and gasohol

**Color:**

Green

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No

**Fiig:**

A09700