NSN 8010-00-515-2211

Primer Coating - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/8010-00-515-2211

Specific Use:

Corrosion resistive primer

Application Method:

Brushing as packaged or brushing, after thinning or spraying as is or spraying after thinning

Quantity Within Each Unit Package:

5.000 gallons

Features Provided:

Lead free

Pigment Material Type:

Zinc chromate

Rated Drying Time:

15.000 minutes

Volatile Organic Compound In Grams Per Liter:

340.0

Special Features:

For use on aluminum and aluminum alloy structures and surfaces and on surfaces pretreated with mil-c-8514 or dod-p-15328 coating

Color:

Yellow

Specification Or Standard:

1 type and c class

Shelf Life:

N/a

Unit Of Measure:

Demilitarization:

No

Fiig:

A09700