

View Online at <https://aerobasegroup.com/nsn/8010-01-096-0681>

Specific Use:

Corrosion resistive primer

Application Method:

Brushing as packaged or roller or spraying as is

Quantity Within Each Unit Package:

1.000 gallons

Pigment Material Type:

Zinc dust

Vehicle Material Type:

Silicone resin

Pigment Separate Package Type:

Container

Rated Drying Time:

Between 6.000 hours and 8.000 hours

Volatile Organic Compound In Grams Per Liters:

395.5

Special Features:

Heat resistant; for use on metal surfaces operating at temperatures from 500 to 1000 degrees f, with intermittent use to 1200 degrees f

Color:

Gray, dark

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A09700