

View Online at <https://aerobasegroup.com/nsn/8010-01-193-0519>

Specific Use:

Metal

Application Method:

Spraying as is or spraying after thinning

Content Within Each Unit Package:

Consists of 1-1/2 pints of component a (pigmented epoxy resin) and 1/2 pint of component b (curing agent) to produce 1 quart

Features Provided:

Lead free and chromate free

Vehicle Material Type:

Epoxy resin

Rated Drying Time:

45.000 minutes

Volatile Organic Compound In Grams Per Liter:

340.0

Environmental Attribute Code:

Low volatile organic compound - coatings - metal parts coatings

Special Features:

Basic corrosion performance; water reducible; corrosion inhibiting; compatible with chemical agent resistant aliphatic polyurethane topcoats

Color:

Gray, light

Supplementary Features:

Mil-dtl-53030 type 1 formulation has been removed from this specification and replaced with the type 2 formulation; use nsn 8010-01-603-2126 for future procurement

Specification Or Standard:

1 type

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli

Fiig:

A09700

Mil-std (military Standard):

Mil-dtl-53030 spec.