

View Online at <https://aerobasegroup.com/nsn/8010-01-193-0519>

**Specific Use:**

Metal

**Application Method:**

Spraying as is or spraying after thinning

**Content Within Each Unit Package:**

Consists of 1-1/2 pints of component a (pigmented epoxy resin) and 1/2 pint of component b (curing agent) to produce 1 quart

**Features Provided:**

Lead free and chromate free

**Vehicle Material Type:**

Epoxy resin

**Rated Drying Time:**

45.000 minutes

**Volatile Organic Compound In Grams Per Liter:**

340.0

**Environmental Attribute Code:**

Low volatile organic compound - coatings - metal parts coatings

**Special Features:**

Basic corrosion performance; water reducible; corrosion inhibiting; compatible with chemical agent resistant aliphatic polyurethane topcoats

**Color:**

Gray, light

**Supplementary Features:**

Mil-dtl-53030 type 1 formulation has been removed from this specification and replaced with the type 2 formulation; use nsn 8010-01-603-2126 for future procurement

**Specification Or Standard:**

1 type

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli

**Fiig:**

A09700

**Mil-std (military Standard):**

Mil-dtl-53030 spec.