NSN 8010-01-286-9499

Mil-p-23377 spec.

Epoxy Primer Coating Kit - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/8010-01-286-9499

view offilite at https://defobasegroup.com/hish/outo-out-200-9499
Application Method:
Spraying as is or spraying after thinning
Quantity Within Each Unit Package:
1.000 quarts
Content Within Each Unit Package:
Consists of component a (epoxy resin and solvents) and component b (polyamide and/or amine resin and solvents) to equal 1 quart
Pigment Material Type:
Strontium chromate
Vehicle Material Type:
Epoxy resin and polyamide resin
Rated Drying Time:
5.000 hours
Volatile Organic Compound In Grams Per Liter:
340.0
Environmental Attribute Code:
Low volatile organic compound - coatings - aerospace operations coatings
Special Features:
Standard pigments; for general use as a corrosion inhibitive, chemical resistant, strippable primer
Color:
Yellow
Specification Or Standard:
1 type and c2 class
Shelf Life:
N/a
Unit Of Measure:
Demilitarization:
Yes - demil/mli
Fiig:
A09700
Mil-std (military Standard):