## NSN 8010-01-300-0609

Enamel - Page 1 of 1

**Unit Of Measure:** 

Demilitarization:

No Fiig: A09700



View Online at https://aerobasegroup.com/nsn/8010-01-300-0609 Specific Use: Protective coating, electronic equipment **Application Method:** Spraying as is or dipped or baked on **Quantity Within Each Unit Package:** 1.000 gallons **Gloss Designation:** Gloss **Rated Drying Time:** 4.000 hours **Special Features:** Oil and salt spray resistant; 4 hour air drying time; 1 to 2 hour bake time at 150 to 200 degrees f; for interior surfaces of electrical equipment Color: Black Shelf Life: N/a