

View Online at <https://aerobasegroup.com/nsn/8010-01-441-6135>

Specific Use:

Metal

Application Method:

Brushing as packaged or roller or spraying as is

Quantity Within Each Unit Package:

1.000 gallons

Pigment Material Type:

Iron oxide and zinc dust

Vehicle Material Type:

Polyurethane

Recoating Air Drying Time:

4.0 hours

Rated Drying Time:

30.000 minutes

Volatile Organic Compound In Grams Per Liters:

340.0

Special Features:

Single component; moisture curing; for use on ferrous and galvanized metals in marine and industrial environments; 30 minute tack free dry time at 75 degrees f; 7 day full cure time

Color:

Green

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A09700