

View Online at <https://aerobasegroup.com/nsn/8010-01-441-6140>

Specific Use:

Marinemarine

Application Method:

Brushing as packaged or roller or spraying as is

Quantity Within Each Unit Package:

1.000 gallons

Features Provided:

Chromate free and flammable

Gloss Designation:

Flat

Basic Formulation Type:

Polyurethane

Rated Drying Time:

30.000 minutes

Volatile Organic Compound In Grams Per Liter:

340.0

Special Features:

Single component; moisture curing; for use as intermediate coating over existing epoxy, vinyl, alkyd, phenolic and red lead coatings; 30 minute tack free dry time at 75 degrees f; 7 day full cure time

Color:

Red, oxide

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A09700