

View Online at <https://aerobasegroup.com/nsn/8010-01-461-5092>

Application Method:

Sprayed

Shade Identification:

27886

Quantity Within Each Unit Package:

5.000 gallons

Usage Design:

General use abrasive deck coating

Finish For Which Formulated:

Rough

Environmental Attribute Code:

Low volatile organic compound - coatings - marine operations coatings

Special Features:

Standard durability formula; includes primer, intermediate and color topping coats; 18 hr maximum dry time for primer and intermediate coats, 24 hr maximum dry time for color topping coat; 340 grams per liter maximum voc for primer and intermediate coats, 420 grams per liter maximum voc for color topping coat

Color:

White

Specification Or Standard:

4 type and g composition

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A536w0

Mil-std (military Standard):

Mil-prf-24667 spec.