## NSN 8010-01-484-4743

**Fiig:** A09700

Mil-std (military Standard):

Mil-c-53039 spec.



Polyurethane Coating - Page 1 of 1 View Online at https://aerobasegroup.com/nsn/8010-01-484-4743 **Application Method:** Brushing as packaged or spraying as is or spraying after thinning **Quantity Within Each Unit Package:** 1.000 gallons **Features Provided:** Lead free and chromate free **Gloss Designation:** Flat **Coloring Method:** Pigmented **Basic Formulation Type:** Polyurethane **Rated Drying Time:** 30.000 minutes **Color Chip Number:** 33538 **Volatile Organic Compound In Grams Per Liter:** 420.0 **Environmental Attribute Code:** Low volatile organic compound - coatings - metal parts coatings **Special Features:** Chemical agent resistant coating (carc); single component; siliceous flattening agent; for use as a finish coat on military combat equipment Color: Yellow **Specification Or Standard:** 1 type Shelf Life: N/a **Unit Of Measure: Demilitarization:** Yes - demil/mli