

View Online at <https://aerobasegroup.com/nsn/8010-01-486-7550>

Application Method:

Spraying after thinning or spraying as is

Quantity Within Each Unit Package:

1.000 pints

Content Within Each Unit Package:

Component a and component b

Features Provided:

Chromate free

Gloss Designation:

Semigloss

Pigment Material Type:

Rutile titanium dioxide and yellow iron oxide and red iron oxide, dark and carbon black

Vehicle Material Type:

Epoxy resin and polyamide resin

Finish For Which Formulated:

Fine

Rated Drying Time:

4.000 hours

Color Chip Number:

20450

Volatile Organic Compound In Grams Per Liter:

340.0

Color:

Brown

Test Data Document:

81349-mil-c-22750 specification (includes engineering type bulletins, brochures, etc., that reflect specification type data in specification format; excludes commercial catalogs, industry directories, and similar trade publications, reflecting general type data on certain environmental and performance requirements and test conditions that are shown as "typical", "average", "", etc.).

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli

Fiig:

A09700

Mil-std (military Standard):

Mil-c-22750 spec.