NSN 8010-01-493-3177

Polyurethane Coating - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/8010-01-493-3177

| Application Method: |
|---|
| Brushing as packaged or spraying after thinning |
| Quantity Within Each Unit Package: |
| 3.000 quarts |
| Content Within Each Unit Package: |
| Consists of 2 quarts of component a and 1 quart of component b to equal 3 quarts |
| Features Provided: |
| Lead free and chromate free |
| Gloss Designation: |
| Flat |
| Coloring Method: |
| Pigmented |
| Rated Drying Time: |
| 30.000 minutes |
| Color Chip Number: |
| 33446 |
| Volatile Organic Compound In Grams Per Liters: |
| 220.0 |
| Environmental Attribute Code: |
| Low volatile organic compound - coatings - metal parts coatings |
| Special Features: |
| Polymeric flattening agent; water dispersible; for use as a chemical agent resistant finish coat on all military tactical equipment |
| Color: |
| Tan |
| Specification Or Standard: |
| 2 type |
| Shelf Life: |
| N/a |
| Unit Of Measure: |
| |
| Demilitarization: |
| Yes - demil/mli |
| Fiig: |
| A09700 |
| Mil-std (military Standard): |
| Mil-dtl-64159 spec. |