## NSN 8010-01-493-3197

Polyurethane Coating - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/8010-01-493-3197

| Application Method:   |
|---|
| Brushing as packaged or spraying after thinning   |
| Quantity Within Each Unit Package:  |
| 3.000 quarts  |
| Content Within Each Unit Package:   |
| Consists of 2 quarts of component a and 1 quart of component b to equal 3 quarts  |
| Features Provided:  |
| Lead free and chromate free   |
| Gloss Designation:  |
| Flat  |
| Coloring Method:  |
| Pigmented   |
| Rated Drying Time:  |
| 30.000 minutes  |
| Color Chip Number:  |
| 36300   |
| Volatile Organic Compound In Grams Per Liters:  |
| 220.0   |
| Environmental Attribute Code:   |
| Low volatile organic compound - coatings - metal parts coatings   |
| Special Features:   |
| Polymeric flattening agent; water dispersible; for use as a chemical agent resistant finish coat on all military tactical equipment |
| Color:  |
| Gray  |
| Specification Or Standard:  |
| 2 type  |
| Shelf Life:   |
| N/a   |
| Unit Of Measure:  |
|   |
| Demilitarization:   |
| Yes - demil/mli   |
| Fiig:   |
| A09700  |
| Mil-std (military Standard):  |
| Mil-dtl-64159 spec.   |